

Beltech 250

Product Data Sheet June 2014

A woven geotextile fabric, produced from polypropylene slit-film tapes, which will meet or exceed the following MARV's. This fabric is produced for use in AASHTO M-288 Class 2 and other separation applications.

Property	Test Method	English Units			SI Units		
		MARV			MARV		
		MD	CD		MD	CD	
Grab Tensile Strength	ASTM D-4632	250	250	lbs	1113	1113	N
Grab Tensile Elongation	ASTM D-4632	15	15	%	15	15	%
Wide Width Tensile Ultimate	ASTM D-4595	n/a	n/a	lbs/in	n/a	n/a	kN/m
Wide Width Elongation	ASTM D-4595	n/a	n/a	%	n/a	n/a	%
Trapezoid Tear	ASTM D-4533	90	90	lbs	401	401	N
Puncture	ASTM D-4833	100		lbs	445		N
CBR Puncture - Typical Value	ASTM D-6241	1000		lbs	4450		N
Permittivity	ASTM D-4491	0.05		sec ¹	0.05		sec"1
A.O.S.	ASTM D-4751	30		U.S. Sieve	0.6		mm
UV Resistance (500 hrs)	ASTM D-4355	80		%	80		%
Water Flow Rate	ASTM D-4491	4		gal/min/ft ²	163		I/min/m ²

		English Units			SI Units				
Packaging	Width	Area	Length	Width	Area	Length			
	(feet)	(yard ²)	(yard)	(m)	(m ²)	(m)			
Standard Roll Sizes	12.5	600	144	3.8	502	132			
	15	600	120	4.6	502	110			
	17.5	600	103	5.3	502	94			
Note: Custom sizes are available. Please inquire.									



Produced in Belton, South Carolina, U.S.A.

The foregoing is believed to be an accurate representation of information complied from inside and/or outside sources, however, because test values, statistical data, and other information presented may be based solely on results of unverified tests made on random samples, information presented may relate only to tested samples and because the conditions in which such information may be used are beyond the control of Belton Industries, Inc., Belton does not guarantee either the accuracy or reliability of the information or the suggestions and recommendations contained herein. Belton assumes no responsibility for the use of information presented herein and hereby disclaims all liabilities which may arise in connection with the use of information herein presented. All specifications, properties, values, statistical data and applications listed herein are provided as information only, without charge or obligation to the recipient or user, and in no way either makes or creates any warranty with respect to any product or modifies, amends or enlarges any warranty made with respect to any product. Final determination of the suitability, reliability and accuracy of the information and suggested uses is solely the responsibility of the user. The property values expressed are effective on the date shown above, supersede any values previously published, and are subject to change without notice.

