

CSB-Series Silt Bag

VDOT Approved Nonwoven Silt Filtration Bag

SPECIFICATIONS

Property	Test Method	Spec
Weight	ASTM D-3776	10.0 oz./sy
Tensile Strength	ASTM D-4632	250 lbs
Elongation @ Break	ASTM D-4632	50%
Mullen Burst	ASTM D-3786	400 psi
Puncture Strength	ASTM D-6241	700 lbs
Trapezoidal Tear	ASTM D-4533	100 lbs
Apparent Opening Size	ASTM D-4751	100 US Sieve
Permittivity	ASTM D-4491	1.2 sec-1
Water Flow Rate	ASTM D-4491	85 gal/min/sf
U.V. Resistance % retained (500 hrs)	ASTM D-4355	70%

Test results represent Minimum Average Roll Values (MARV) with the exception of weight which is a typical result.

Available Sizes

CSB-4	4' X 6'
CSB-12	12' X 12'
CSB-15	15' X 15'
CSB-30	15' X 30'

Distributed by Colonial Construction Materials, Inc.

1071 Merchants Lane Oilville, VA 23129

P. 804-264-0128 F. 804-708-0269

www.colonial-materials.com