

# SKAPS GT-110

NON-WOVEN GEOTEXTILE



## SKAPS INDUSTRIES

335 Athena Drive,  
Athens, GA 30601  
Ph: (706)-354-3700  
Fax: (706)-354-3737  
Email: contact@skaps.com

SKAPS GT-110 is a needle-punched nonwoven geotextile made of 100% virgin polypropylene staple fibers, which are formed into a random network for dimensional stability. SKAPS GT-110 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered alkalis and acids. Polypropylene is stable within the pH range of 2 to 13. SKAPS GT-110 is NTPEP certified and meets requirements as per AASHTO Standards and/or D.O.T. Standards.

SKAPS GT-110 conforms to the Minimum Average Roll Values (MARV) listed below:

PROPERTY	TEST METHOD	ENGLISH (MARV <sup>2</sup> )	METRIC (MARV <sup>2</sup> )
Grab Tensile Strength	ASTM D 4632	250 lbs.	1.112 kN
Grab Elongation	ASTM D 4632	50%	50%
Trapezoid Tear Strength	ASTM D 4533	100 lbs.	0.444 kN
CBR Puncture Resistance	ASTM D 6241	700 lbs.	3.113 kN
Permittivity <sup>4</sup>	ASTM D 4491	1.2 sec <sup>-1</sup>	1.2 sec <sup>-1</sup>
Water Flow <sup>4</sup>	ASTM D 4491	80 gpm/ft <sup>2</sup>	3251 l/min/m <sup>2</sup>
Apparent Opening Size (AOS) <sup>3&amp;4</sup>	ASTM D 4751	100 Std. U.S. Sieve	0.150 mm
UV Resistance	ASTM D 4355	70%/500 hrs.	70%/500 hrs.

### PACKAGING

Roll Dimensions (W x L)	12.5 x 360 ft. 15 x 300 ft.	3.81 m x 109.8 m 4.6 m x 91.4 m
Area Per Roll	500 sq. yards	418.3 sq. meters
Estimated Roll Weight	320 lbs.	145 kg

### NOTES:

1. The property values listed above are subject to change without notice.
2. Minimum Average Roll Values (MARV) is calculated as the average minus two standard deviations. Statistically, it yields approximately 97.5% degree of confidence that any samples taken from quality assurance testing will meet or exceed the values described above.
3. Maximum Average Roll Value (MaxARV)
4. At time of manufacturing. Handling may change these properties.

*This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.*