



SKAPS INDUSTRIES

335 Athena Drive, Athens, GA 30601 Ph: (706)-354-3700 Fax: (706)-354-3737 Email: contact@skaps.com

SKAPS GT-170 is a needle-punched nonwoven geotextile made of 100% virgin polypropylene staple fibers, which are formed into a random network for dimensional stability. SKAPS GT-170 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered alkalis and acids. Polypropylene is stable within the pH range of 2 to 13. SKAPS GT-170 is NTPEP certified and meets requirements as per AASHTO Standards and/or D.O.T. Standards.

PROPERTY	TEST METHOD	ENGLISH (MARV ²)	METRIC (MARV ²)
Grab Tensile Strength	ASTM D 4632	180 lbs.	0.800 kN
Grab Elongation	ASTM D 4632	50%	50%
Trapezoid Tear Strength	ASTM D 4533	75 lbs.	0.333 kN
CBR Puncture Resistance	ASTM D 6241	475 lbs	2.113 kN
Permittivity4	ASTM D 4491	1.4 sec ⁻¹	1.4 sec ⁻¹
Water Flow ⁴	ASTM D 4491	105 gpm/ft ²	4278 l/min/m ²
Apparent Opening Size (AOS) ^{3&4}	ASTM D 4751	70 Std. U.S. Sieve	0.212 mm
UV Resistance	ASTM D 4355	70%/500 hrs.	70%/500 hrs.

SKAPS GT-170 conforms to the Minimum Average Roll Values (MARV) listed below:

PACKAGING

Roll Dimensions (W x L)	12.5 x 360 ft. 15 x 300 ft.	3.81 m x 109.8 m 4.6 m x 91.4 m
Area Per Roll	500 sq. yards	418.3 sq. meters
Estimated Roll Weight	220 lbs.	100 kg

NOTES:

- 1. The property values listed above are subject to change without notice.
- 2. Minimum Average Roll Values (MARV) is calculated as the average minus two standard deviations. Statistically, it yields approximately 97.5% degree of confidence that any samples taken from quality assurance testing will meet or exceed the values described above.
- 3. Maximum Average Roll Value (MaxARV)
- 4. At time of manufacturing. Handling may change these properties.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.