

Woven Belted Silt Fence 2 Stage

2 STAGE (WBSF2S) Test Method	Storm Water Release Stage (Above Clean Out Point)		Sedimentation Filter Stage (closest to ground)		Trenched area (Underground)	
	20-sieve zone		50-sieve zone		30-sieve zone	
	MD	XD	MD	XD	MD	XD
ASTM D4632(Grab)(Lbs) MARV*:	320	180	425	180	375	180
ASTM D4632(Grab)(%) MARV*:	15	15	15	15	15	15
ASTM D4533(Trap)(Lbs) MARV*:	90	60	130	60	110	60
ASTM D4491(Permittivity) Minimum Test Value*:	258 gpm/ft ² 3.50 sec-1		81 gpm/ft ² 1.10 sec-1		129 gpm/ft ² 1.75 sec-1	
ASTM D4751(AOS)MaxAVR(mm) Maximum Test Value*:	0.850		0.300		0.600	
ASTM D6241(50mm Puncture)(Lbs) MARV*:	650		650		650	
ASTM D5261(Mass/Area)(oz/sq.yd) Typical Value*:	5.0		6.6		5.9	
ASTM D4355(% retained at 500 hours) Typical Value*:	80	80	80	80	80	80

1. Minimum Average Roll Value, unless otherwise stated. Values effective 5.7.2019. Values may change without notice.
2. This information related to the specific material designated and may not be valid for such material used in combination with any other materials or in any process.
3. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date of manufacture. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself or herself as to the suitability and completeness of such information for his or her own particular use.
4. We do not accept liability or damage that may occur from the use of this information, nor do we offer any warranty against infringement.

Distributed by Colonial Construction Materials Inc.

1071 Merchants Lane Oilville, VA 23129

Ph. 800-436-6287

www.colonial-materials.com